



Architectural Window Film Specifications

| Product | VLT | TSER | Visible Light Reflectance | IR Rejection (900-1000nm) | UV Rejection | SC | SHGC | U-Value (W/m ² K) | Heat Absorption Rate | Tensile Strength (N/10mm) | Elongation At Break |
|-------------------|-----|------|---------------------------|---------------------------|--------------|-----|------|------------------------------|----------------------|---------------------------|---------------------|
| Platinum Air7090 | 70% | 42% | - | 88% | 99% | .70 | .58 | 6.03 | 52.4% | - | - |
| Platinum 5099 | 50% | 51% | 6.8% | 99% | 99% | .58 | .49 | 6.0 | 66.4% | - | - |
| Platinum 3599 | 35% | 55% | 6.8% | 99% | 99% | .52 | .45 | 6.0 | 76.6% | - | - |
| Rescue 4mil | 89% | - | 7% | - | 97% | - | - | - | 11.1% | 140 | 111% |
| Trinity 5099 4mil | 50% | 51% | 6.8% | 99% | 99% | .58 | .49 | 6.0 | 65.3% | 140 | 111% |

Contact Rayno Window Film at [844-RAY-FILM](tel:844-749-3462). Visit raynofilm.com for more details