



## MonoCarbon Window Film Specifications

Product	NET VLT	Fading Rate	TSER	Visible Light Reflection		UV Rejection	IR Rejection	Glare Reduction	SC	SHGC
				Interior	Exterior					
MonoCarbon 2Ply	5%	< 1%	54.0%	5.0%	5.2%	99.9%	72%	95%	.52	.46
	20%	< 1%	42.0%	5.3%	5.4%	99.9%	50%	75%	.66	.58
	35%	< 1%	35.0%	5.7%	5.8%	99.9%	41%	59%	.75	.65
	50%	< 1%	28.0%	6.4%	6.2%	99.9%	34%	42%	.82	.72

Contact **Rayno Window Film** at **844-RAY-FILM**. Visit [raynofilm.com](http://raynofilm.com) for more details